

# PATENT ABSTRACTS OF JAPAN

(11)Publication number : 11-268208

(43)Date of publication of application : 05.10.1999

(51)Int.Cl.

B32B 27/32  
B32B 27/28  
B32B 27/30  
C08L 23/02  
C08L 25/04  
// B32B 15/08

(21)Application number : 10-073918

(71)Applicant : SUMIKA PLASTECH KK

(22)Date of filing : 23.03.1998

(72)Inventor : MITSUI SHINICHI

## (54) LAMINATED FILM, LID MEMBER AND CONTAINER

### (57)Abstract:

**PROBLEM TO BE SOLVED:** To show an easy peelability, and an easy openability, and provide a separation interface which is excellent in the appearance by a method wherein a specified sealant layer, a cohesive failure layer, and a supporting layer are respectively formed of a layer containing one kind of a resin which is selected from styrene-based resins, and olefin-based resins.

$$K + L = 100$$

**SOLUTION:** A sealant layer is constituted of one kind from styrene/ethylene/ propylene-based resins, a cohesive failure layer is constituted of an olefin/olefin-based resin composition X, and a supporting layer is constituted of a layer containing an olefin/olefin based resin composition Y. Also, the olefin based resin/the

$$35 \leq 0.2 \times K + 0.8 \times M \leq 55$$

same composition X contains a component B, and satisfies formulas I, II. In the formulas I, II, K and L represent the blending amounts of the components A, B, and M represents the content of a repeating unit from a vinyl monomer in the ethylene based polymer respectively. A is one kind or a mixture of two or more kinds of one kind or more of a vinyl monomer selected from unsaturated carboxylic acids or the like, and an ethylene-based polymer of a repeating unit induced from ethylene, B is an ethylene/propylene- based resin, and Y is an

ethylene/propylene based resin.